



Proseal 303

Brushable and sprayable MS Polymer based sealant developed for body seam sealing, noise reduction coatings and OEM stone protection of sills, underbody and wheelhouses. Compatible with leading automotive paints.



Features & Benefits

- Isocyanate and solvent free
- Medium to low viscosity - replicates the smooth OEM structure on sills
- Good spray ability - easy to apply with little or no overspray
- Excellent finish structure - replicates OEM finish
- Relatively fast skinning / cure speed - fast paint over & allows handling after short time
- Good paint adhesion with leading automotive paint technologies

P/N	Product	S/C	Packaging
85119	Proseal 303 Black	KPS303B	290 ml cartridge
85616	Proseal 303 Grey	KPS303G	290 ml cartridge
85473	Proseal 303 Beige	KPS303	290 ml cartridge
84325	Multi Gun	KMG	1 unit
84788	Multi Gun nozzles (for bead extrusion only)		10 round nozzles and 10 rectangular nozzles
86667	Ribbed Seam Nozzle		12 nozzles

Application

KENT Proseal 303 has been developed to meet the needs of Body shops to replicate the distinctive finish of the sprayed seam sealers used by OEM's in the manufacture of many vehicles.

Together with the Multi Gun, a variety of finishes can be obtained to match the diverse styles of Volkswagen, Citroen, Renault and many far eastern vehicles.

Application areas include sills, boot and rear panel areas and around front suspension turrets. The black version is ideal for applications where overpainting is not required e.g. underbody and wheelhouses.

Proseal 303 also doubles as a general sealer, albeit of a higher viscosity than Proseal 404.

N.B.: Apply paint system according to the advice of paint manufacturer. A compatibility test is recommended. KENT Epoxy Primer, KENT Graphene Primer or KENT Ultrafill 3 can be used as a barrier layer before painting (follow instructions in our TDS).

Instructions

1. Clean surface with KENT Acrysol or Soft Surface Cleaner and allow to dry.
2. Spray Proseal 303 with KENT Multi Gun, adjusting the pressure to suit the application (see gun instructions).
3. Paint, if required, once skin has formed (after app. 30 minutes in standard conditions). Paint within 4 hours. In case of a longer waiting time, it is necessary to slightly sand Proseal before painting.



Technical Information

Base:	MS Polymer based adhesive sealer
Consistency:	Smooth low viscosity paste
Colour:	Black / Grey / Beige
Shelf Life:	18 months
Customs Tariff Code:	3214 10 10
VOC:	32 g/l

Cure mechanism:	Moisture cure	Green strength:	n/a
Specific gravity:	1.6 g/ml	Tensile strength (100%):	1.4 MPa (DIN 53504/ISO 37)
Viscosity:	approx 200 Pa.s	Tensile strength (at break):	1.7 MPa (DIN 53504/ISO 37)
Skin forming time:	approx. 15 mins (20°C/50%RH)	Elongation at break:	150 % (DIN 53504/ISO 37)
Open time:	approx. 15 mins (20°C/50%RH)	Shear stress:	n/a
Cure speed @ 24 hours:	3 mm (20°C/50%RH)	Tear propagation:	n/a
Shore A:	approx. 50 (DIN 53505)		
Volume change:	<3% (DIN 52451)		
Application temp:	+5°C to +35°C		
Temp resistance :	-40°C to +120°C (Max 180°C for 0.5 hour)		



SDS available on www.kenturope.com

Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of KENT (United Kingdom) Ltd. This data sheet and its contents (the "Information") belong to KENT (United Kingdom) Ltd, or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including

liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. KENT is the trading name of KENT (United Kingdom) Ltd.

Registered Office: Amber House,
Showground Road, Bridgewater, Somerset, United Kingdom TA6 6AJ
All rights reserved

KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Drive, Pitreavie Business Park, Dunfermline, Fife KY11 8US Tel : 0800 136925 or 01383 723344 between 08:30-17:30
Monday-Thursday, 09:00-15:00 on Fridays'. For out of hours queries please Fax us on 01383 735829 or Email: KENTsales.UK@kenturope.com

REV: 30/06/2021